ECONOMY UNDERCOAT

Updated Feb'20

Economy Undercoat is a quick-drying oil-modified alkyd based undercoat with good build.

Paint Type	Product Type	Finishing	Recommended Substrate	Pack Size		
Solvent based	Interior & Exterior	Matt	Wood and Metal	5 Litres, 7 Litres, 20 Litres		
Composition						
Pigment	: Titanium dioxide and mineral extenders					
Binder	: Modified long oil alkyd					
Thinner	: Hydrocarbon					
Technical Data						
Drying Time	: Touch Dry	: 12 minutes				
	: Hard Dry	: 2 hours				
			n temperature 28 – 32 °C, humidity 3	70 – 80% and 5% dilution with		
		Nippon General Purpose Thinner.				
Recoating Time	: 4 hours					
	-		d on temperature 28 – 32 °C, humid	ity 70 – 80% and 5% dilution		
*Important Note:	with Nippor	General Purpos	e ininner.			
	ina time are str	onaly depending	on environment ventilation paint th	nickness environment		
Drying Time and recoat			on environment ventilation, paint th			
Drying Time and recoat	ent humidity, n	umber of coats a	pplied, thinner used to dilute produc			
Drying Time and recoat temperature, environm drying time and recoati	ent humidity, n ing time provide	umber of coats a ed is for guide onl	pplied, thinner used to dilute produc ly.			
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness	ent humidity, n ing time provide : Around 50	umber of coats a ed is for guide onl	pplied, thinner used to dilute produc			
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats	ent humidity, n ing time provide : Around 50 : 1 coat	umber of coats a ed is for guide onl - 60 μm per coat	oplied, thinner used to dilute produc y. (based on substrate condition)	t and recoat materials. So		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ²	umber of coats a ed is for guide onl - 60 μm per coat per litre per coat	oplied, thinner used to dilute produc ly. (based on substrate condition) : (Actual coverage is dependent on	t and recoat materials. So		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats Theoretical Coverage	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a	umber of coats a ed is for guide onl - 60 μm per coat per litre per coat	oplied, thinner used to dilute produc y. (based on substrate condition)	t and recoat materials. So		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a : ~ 52%	umber of coats a ed is for guide onl - 60 μm per coat per litre per coat	oplied, thinner used to dilute produc y. (based on substrate condition) : (Actual coverage is dependent on ion and finishing appearance)	t and recoat materials. So		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats Theoretical Coverage Volume Solid Shelf Life	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a : ~ 52% : Up to 12 m	umber of coats a ed is for guide onl - 60 μm per coat per litre per coat pplication conditi	oplied, thinner used to dilute produc y. (based on substrate condition) : (Actual coverage is dependent on ion and finishing appearance)	t and recoat materials. So		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats Theoretical Coverage Volume Solid Shelf Life Application Methor	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a : ~ 52% : Up to 12 m	umber of coats a ed is for guide onl - 60 μm per coat per litre per coat pplication conditi nonths in tight sea	oplied, thinner used to dilute produc ly. (based on substrate condition) (Actual coverage is dependent on ion and finishing appearance) aled container	t and recoat materials. So substrate condition, applicatior		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats Theoretical Coverage Volume Solid Shelf Life	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a : ~ 52% : Up to 12 m	umber of coats a ed is for guide onl - 60 μm per coat per litre per coat pplication conditi nonths in tight sea	oplied, thinner used to dilute produc y. (based on substrate condition) : (Actual coverage is dependent on ion and finishing appearance)	t and recoat materials. So substrate condition, applicatior		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats Theoretical Coverage Volume Solid Shelf Life Application Metho Brush / Roller	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a : ~ 52% : Up to 12 m d : The paint in Thinner.	umber of coats a ed is for guide onl - 60 μm per coat per litre per coat pplication condition toonths in tight sea s ready for use af	oplied, thinner used to dilute produc y. (based on substrate condition) : (Actual coverage is dependent on ion and finishing appearance) aled container	t and recoat materials. So substrate condition, applicatior hin with 5% of General Purpose		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats Theoretical Coverage Volume Solid Shelf Life Application Metho Brush / Roller Conventional Air Spray	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a : ~ 52% : Up to 12 m d : The paint i Thinner. : Dilute the	umber of coats a ed is for guide onl - 60 μm per coat per litre per coat pplication condition toonths in tight sea s ready for use af	oplied, thinner used to dilute produc y. (based on substrate condition) : (Actual coverage is dependent on ion and finishing appearance) aled container ter thorough stirring. If necessary, t pre than 15 – 20 % of General Purpo	t and recoat materials. So substrate condition, applicatior hin with 5% of General Purpose		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats Theoretical Coverage Volume Solid Shelf Life Application Metho Brush / Roller Conventional Air Spray Airless Spray	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a : ~ 52% : Up to 12 m d : The paint i Thinner. : Dilute the p : The paint i	umber of coats a ed is for guide onl - 60 μm per coat per litre per coat pplication condition toonths in tight sea s ready for use af	oplied, thinner used to dilute produc y. (based on substrate condition) : (Actual coverage is dependent on ion and finishing appearance) aled container	t and recoat materials. So substrate condition, applicatior hin with 5% of General Purpose		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats Theoretical Coverage Volume Solid Shelf Life Application Metho Brush / Roller Conventional Air Spray Airless Spray Recommended Coa	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a : ~ 52% : Up to 12 m d : The paint i Thinner. : Dilute the p : The paint i	umber of coats a ed is for guide onl - 60 μm per coat per litre per coat pplication condition toonths in tight sea s ready for use af	oplied, thinner used to dilute produc y. (based on substrate condition) : (Actual coverage is dependent on ion and finishing appearance) aled container ter thorough stirring. If necessary, t pre than 15 – 20 % of General Purpo	t and recoat materials. So substrate condition, applicatior hin with 5% of General Purpose		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats Theoretical Coverage Volume Solid Shelf Life Application Methoo Brush / Roller Conventional Air Spray Airless Spray Recommended Coa Wood	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a : ~ 52% : Up to 12 m d : The paint in Thinner. : Dilute the : The paint in	umber of coats a ed is for guide onl - 60 µm per coat per litre per coat pplication conditi nonths in tight sea s ready for use af paint with not mo s ready for use af	oplied, thinner used to dilute produc y. (based on substrate condition) (Actual coverage is dependent on ion and finishing appearance) aled container ter thorough stirring. If necessary, t ore than 15 – 20 % of General Purpo ter thorough stirring.	t and recoat materials. So substrate condition, application hin with 5% of General Purpose ise Thinner.		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats Theoretical Coverage Volume Solid Shelf Life Application Metho Brush / Roller Conventional Air Spray Airless Spray Recommended Coa Wood Primer / Sealer	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a : ~ 52% : Up to 12 m d : The paint is Thinner. : Dilute the p : The paint is the paint is ating System : 9000 Alum	umber of coats a ed is for guide onl - 60 µm per coat per litre per coat pplication conditi nonths in tight sea s ready for use af paint with not mo s ready for use af	oplied, thinner used to dilute produc y. (based on substrate condition) (Actual coverage is dependent on ion and finishing appearance) aled container ter thorough stirring. If necessary, t ore than 15 – 20 % of General Purpo ter thorough stirring.	t and recoat materials. So substrate condition, application hin with 5% of General Purpose se Thinner. : 1 Coat		
Drying Time and recoat temperature, environm drying time and recoati Dry Film Thickness No. of Coats Theoretical Coverage Volume Solid Shelf Life Application Methoo Brush / Roller Conventional Air Spray Airless Spray Recommended Coa Wood	ent humidity, n ing time provide : Around 50 : 1 coat : 9 – 11 m ² method, a : ~ 52% : Up to 12 m d : The paint i Thinner. : Dilute the : The paint i : The paint i : The paint i	umber of coats a ed is for guide onl - 60 µm per coat per litre per coat pplication conditi nonths in tight sea s ready for use af paint with not mo s ready for use af	oplied, thinner used to dilute produc y. (based on substrate condition) : (Actual coverage is dependent on ion and finishing appearance) aled container ter thorough stirring. If necessary, t ore than 15 – 20 % of General Purpo ter thorough stirring.	t and recoat materials. So substrate condition, application hin with 5% of General Purpose ise Thinner.		



Steel / Iron

Primer / Sealer	: Red Oxide Primer	: 1 Coat
Undercoat	: Economy Undercoat	: 1 Coat
Top Coat	: 9000 Gloss Finish / Q-Lac Gloss Finish	: 2 Coats
Aluminium / Galva	inized Iron	
Etching Primer	: Etching Primer 120 / Galvaprimer	: 1 Coat
Primer / Sealer	: Red Oxide Primer	: 1 Coat
Undercoat	: Economy Undercoat	: 1 Coat
Top Coat	: 9000 Gloss Finish / Q-Lac Gloss Finish	: 2 Coats

Surface Preparation

Wood

Surface must be dry and free from dirt, grease and other contaminants. Smoothen surface with sandpaper and then clean off and dry. The scraped areas should be spot-primed using an undercoat for wood surfaces. Light sanding on surface would ensure better subsequent intercoat adhesion.

Metal

Surface must be dry and free from dirt, grease and other contaminants. Ferrous substrate should be sanded or wire-brushed to remove millscales and rust. Clean off dust and dry. The scraped areas should be spot-primed using a primer for metal. Light sanding on surface would ensure better subsequent intercoat adhesion.

Cleaning

Clean up equipment with water immediately after use.

Safety Precautions

- Keep container tightly closed and keep out of reach children or away from food and drink.
- Ensure good ventilation during application and drying.
- When applying paint, it is advisable to wear eye protection.
- In case of contact with eye, rinse with plenty of water immediately and seek medical advice.
- Remove splashes from skin by using soap or water.
- Paint must always be stored in a cool place.
- When transporting paint, care must be taken. Always keep container in a secure upright position.
- Dispose off any paint waste in accordance with the appropriate Environment Quality Regulations.

Note

* Theoretical Coverage is based on a mathematical formula

$$\left[\frac{Volume \ Solid \ \% \ x \ 10}{Dry \ Film \ Thickness}\right] = m^2/lit/coat$$

and does not consider LOSS FACTORS.

Variables like porosity of substrate, application method, dilution ratio, dry film thickness, opacity and so on will affect the loss factor and can vary from 30% - 50% or even more.

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.

We reserve the right to alter the given without prior notice.